

ref 126-144

Play with the light

Your sign visible night and day, every day.
> In the daytime, the original colour of the sheet.
> At night, when illuminated: white appearance.

The combination of selected additives and a strong and professional light source will create a state of the art signage.

The colour & white effect give an extra dimension to the visibility of illuminated signs.

Easily formed, this translucent PMMA sheet is available in a variety of colours which give a coloured (when not illuminated) and a white (when illuminated) appearance.

Performances

Key benefits



In the daytime, the original colour of the sheet.
By Night, when illuminated: white appearance.
Excellent diffusion properties- Easily formed
Extremely weatherable for outdoor applications
High visibility sign & signage with low energy expenditure

Altuglas® Night & Day are available in :
144.28042 **Black** & White
126.28022 **Grey** & White
126.24078 **Green** & White
126.23097 **Blue** & White

FOR YOUR PROJECT : Your colour can be optimized on request into the Night & Day range.

Applications : Illuminated Signs, Exhibition booth, Stores & walls in architectures...



altuglas.com / altuglas-online.com

ref 126-144

ACRYLIC SHEET

Play with the light

Visibility night and day, every day, for your sign.

- > In the daytime, the original colour of the sheet.
- > At night, when illuminated: white appearance.

Technical Specifications

	Measurement method	Unit	Value
General characteristics			
Density	ISO 1183	g/cm ³	1,19
Water absorption (24H)	ISO 62	%	0,3
Water absorption (8 days)	ISO 62	%	0,5
Mechanical properties			
Modulus of elasticity	ISO 527-2	MPa	3300
Tensile strength (23°C)	ISO 527	kJ/m ²	76
Charpy Impact strength (un-notched)	ISO 179/2D	kJ/m ²	12
Surface hardness (Rockwell scale M)	ISO 2039	-	100
Thermal properties			
Vicat softening point (B50)	ISO 306	°C	115
Coefficient of linear expansion	ISO 11359	mm/m/°C	0,65
Maximum continuous service temperature	-	°C	85
Forming temperature	-	°C	165-190
Optical properties			
Light transmittance (3mm) Depending on reference	ISO 13 468	%	6 to 50
Hiding power	-	-	maximised
Flammability			
Self-ignition temperature		°C	Approx. 450
Melt behaviour when burning		-	Non-drip
Glow wire resistance	EN 60 695-2-11	°C	750
Euroclass classification	EN 13501	-	E
UL	UL 94	-	HB

altuglas.com / altuglas-online.com

The statements, technical information and recommendations obtained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Altuglas International/Arkema expressly disclaims any and all liability. NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OR MERCHANTABILITY, OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN.

The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein should be construed as an inducement to infringe any patent, and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.